


LABORATORIUM JURUSAN TEKNIK MESIN  
UNIVERSITAS MUHAMMADIYAH YOGYAKARTA

AL-AL

Test date	Area mm <sup>2</sup>	Yield point kN	Max. Load kN	Break kN
2007-01	151.747	7.059	12.478	9.939



Yogyakarta, 05 Mei 2017


Material Teknik

Arizona

LABORATORIUM JURUSAN TEKNIK MESIN  
UNIVERSITAS MUHAMMADIYAH YOGYAKARTA

AL-AL

Test date	Area mm <sup>2</sup>	Yield point kN	Max. Load kN	Break kN
2007-01	132.732	17.822	20.243	16.027



Yogyakarta, 05 Mei 2017


Material Teknik

Arizona

LABORATORIUM JURUSAN TEKNIK MESIN  
UNIVERSITAS MUHAMMADIYAH YOGYAKARTA

AL-AL

Test date	Area mm <sup>2</sup>	Yield point kN	Max. Load kN	Break kN
2007-01	132.732	10.645	21.211	16.968



Yogyakarta, 05 Mei 2017


Material Teknik

Arizona

LABORATORIUM JURUSAN TEKNIK MESIN  
UNIVERSITAS MUHAMMADIYAH YOGYAKARTA

AL-AL

Test date	Area mm <sup>2</sup>	Yield point kN	Max. Load kN	Break kN
2007-01	138.929	21.322	33.219	26.574



Yogyakarta, 05 Mei 2017


Material Teknik

Arizona

LABORATORIUM JURUSAN TEKNIK MESIN  
UNIVERSITAS MUHAMMADIYAH YOGYAKARTA

AL-AL

Test date	Area mm <sup>2</sup>	Yield point kN	Max. Load kN	Break kN
2007-01	138.929	17.204	33.659	26.924



Yogyakarta, 05 Mei 2017


Material Teknik

Arizona

LABORATORIUM JURUSAN TEKNIK MESIN  
UNIVERSITAS MUHAMMADIYAH YOGYAKARTA

AL-AL

Test date	Area mm <sup>2</sup>	Yield point kN	Max. Load kN	Break kN
2007-01	149.571	21.218	36.409	29.127



Yogyakarta, 05 Mei 2017


Material Teknik

Arizona

LABORATORIUM JURUSAN TEKNIK MESIN  
UNIVERSITAS MUHAMMADIYAH YOGYAKARTA

AL-AL

Test date	Area mm <sup>2</sup>	Yield point kN	Max. Load kN	Break kN
2007-01	138.929	29.047	32.477	25.981



Yogyakarta, 05 Mei 2017


Material Teknik

Arizona

LABORATORIUM JURUSAN TEKNIK MESIN  
UNIVERSITAS MUHAMMADIYAH YOGYAKARTA

AL-AL

Test date	Area mm <sup>2</sup>	Yield point kN	Max. Load kN	Break kN
2007-01	145.267	25.987	34.923	27.937



Yogyakarta, 05 Mei 2017

Material Teknik


Arizona



LABORATORIUM JURUSAN TEKNIK MESIN  
UNIVERSITAS MUHAMMADIYAH YOGYAKARTA

AL-AL

Test date	Area mm <sup>2</sup>	Yield point kN	Max. Load kN	Break kN
2007-01	138.929	18.585	32.706	26.165



Yogyakarta, 05 Mei 2017

Material Teknik

Arizona